

# THERMO-TEK PS ECO



October 2022

with **ECOSE®**  
TECHNOLOGY



## DESCRIPTION

Thermo-teK PS Eco is a circular-wound rock mineral wool pipe section (pre-formed pipe DN up to 300 mm) with minimum product tolerances of the inner and outer diameters thanks to the use of innovative production technologies. The 1200 mm long pipe section is slit on one side for easier installation.

Due to the product's technical properties, **installation of additional cladding** on pipes is very easy and fast.

Knauf Insulation Thermo-teK PS Eco is produced with **ECOSE® Technology**, a patented binder system, based entirely on renewable raw materials.

## PERFORMANCE

Max. service temperature	450 °C (EN 14707)
Reaction to fire	A <sub>1</sub> (EN 13501-1)
Apparent density	ca. 85-100 kg/m <sup>3</sup> (EN 13470)
Declaration of performance	<a href="http://dopki.com/T4305YPCPR">http://dopki.com/T4305YPCPR</a>

## APPLICATION

Defined Thermo-teK applications:

- Pipe insulation – heating, water supply

The product is recommended for thermal, fire and sound insulation of defined Thermo-teK applications within technical insulation where:

- **good thermal conductivity is needed**
- **fast installation of additional cladding is required**

## BENEFITS


- ✓ Fast and easy installation of additional cladding
- ✓ Minimum tolerances of thicknesses and diameters
- ✓ ECOSE® Technology



## STANDARDS

Knauf Insulation products are produced according to four of the most important International Management Standards for sustainability ISO 9001 (Quality Management), ISO 14001 (Environmental Management), ISO 50001 (Energy Management) and ISO 45001 (Health and Safety Management), all certified by Tüv Nord.

## CERTIFICATES



# THERMO-TEK PS ECO



October 2022

## SPECIFICATIONS

Description	Sign	Description/data					Unit	Standard
Thermal conductivity depending on temperature	g	10	40	50	100	150	°C	ISO 8497
	λ	0,033	0,037	0,039	0,046	0,053	W/(mK)	
Water soluble chloride ions (AS quality)	-	≤ 10					ppm	EN 13468
Water absorption	W <sub>p</sub>	≤ 1					kg/m <sup>2</sup>	EN 13472
Silicone free	-	No emissions of lacquering disturbing substances					-	-
Melting point of fibres	g	≥ 1000					°C	DIN 4102-17
Specific heat capacity	c <sub>p</sub>	1030					J/(kgK)	EN ISO 10456
Designation code	-	MW-EN14303-T8-ST(+)-450-WS1-CL10 (OD < 150 mm)					-	EN 14303
		MW-EN14303-T9-ST(+)-450-WS1-CL10 (OD ≥ 150 mm)						

## HANDLING

Knauf Insulation products are easy to handle and easy to install. They are supplied in suitable packaging materials to balance necessary transport protection with sustainable recycling options. Packaging is not designed for long-term storage or exposure to harsh weather conditions. Further product information is mentioned on every pack.

## STORAGE

For longer-term protection on site we recommend storing the product either indoors or alternatively under a roof cover and off the ground. If covered storage is not available, products can be stored outside (open-air-storage) if placed off the ground (keep palletized) and covered with plastic hood (foil), for a maximum of up to 6 months from the date of delivery. Outdoor storage is not recommended during particularly humid months with large fluctuations in temperature.

## STANDARD FORMATS\*

Thickness	20 -120 mm
Internal diameter	15 - 324 mm
Length	1200 mm

\*Other dimensions on request.



Knauf Insulation mineral wool products made with ECOSE® Technology benefit from a formaldehyde-free binder made from rapidly renewable bio-based materials instead of petroleum-based chemicals. The technology has been developed for Knauf Insulation's mineral wool products, enhancing their environmental credentials without affecting the thermal, acoustic or fire performance. Insulation products made with ECOSE® Technology contain no dye or artificial colours – the colour is completely natural.

## Knauf Insulation d.o.o.

Varaždinska 140, 42220 Novi Marof, Croatia | E-mail: [ts@knaufinsulation.com](mailto:ts@knaufinsulation.com)

All rights reserved, including those of photomechanical reproduction and storage in electronic media. Commercial use of the processes and work presented in this document is not permitted. Extreme caution was taken in assembling the information, texts and illustrations in this document. Nevertheless, errors cannot be entirely ruled out. The publisher and editors assume no legal responsibility or any liability whatsoever for any incorrect information or any consequences thereof. The publisher and editors are grateful for any suggestions for improvement as well as the identification of any errors.