KNAUFINSULATION

KNAUF INSULATION DAP HNF

Needled felts for high end, standard and selfcleaning pyrolytic ovens.



PERFORMANCE

Maximum service temperature

DAP HNF has a maximum service temperature of up to 550/750 °C

Thermal insulation

Optimal thermal insulation properties ensure ideal energy efficiency and energy consumption

Certified quality

LGA Certified Complies with RoHS Directive Complies with REACH Regulation RAL EUCEB

APPLICATION

Insulation of **standard and self-cleaning, pyrolytic ovens** where operating temperatures may reach 750 °C, that meet highest energy efficiency standards.

CERTIFICATES









DESCRIPTION

Knauf insulation DAP NEEDLED FELT HNF

(DAP HNF) products are made of long mineral wool fibres specially needled to form a compact, dimensionally-stable felt with high temperature stability and exceptional thermal insulation properties. Due to its highest insulation performance standards, it can be used for insulating selfcleaning pyrolytic ovens, where operating temperatures may reach as high as 700 °C and at the same time meet highest energy efficient standards. Product dimensions, sections and facing options can all be adapted to customer requirements.

Owing to the unique fibre bonding process, the felts do not contain organic binders or process aids and therefore comply with LGA test for contaminants, valid for mineral fibres in cookers and ovens. With this special production process we are able to guarantee that no emissions of odorous and/or harmful substances are emitted during the use of ovens and cookers even at the highest temperatures.

Needled felts are tested for the presence of the restricted substances and comply to the RoHS directive and REACH regulation.

BENEFITS

- High temperature stability and resistance
- Thermal insulation properties ensure optimal energy efficiency and energy consumption
- ✓ Non-corrosive insulation material (AS Quality)
- Fire protection (European Class A1) material melting point above 1000 °C
- Fire Hazard Classification FHC 0/0
- No organic binders
- Emission-free
- Custom forms and sections
- Optimal composition for high energy efficiency and high performance
- Can be laminated with aluminium foil or glass veil

STANDARD

Technical properties of Knauf Insulation DAP HNF are declared in accordance with EN 14303.

Knauf Insulation DAP HNF is manufactured in accordance with ISO 9001 Quality Management Systems, ISO 14001 Environmental Management Systems, ISO 50001 Energy Management Systems and ISO 45001 Occupational Health and Safety Management Systems as certified by TÜV Nord.



July 2023



KNAUF INSULATION DAP HNF

July 2023

TECHNICAL PROPERTIES

| Characteristics | Symbol | Value | | | | | | | | Unit | Standard |
|---|------------------|---------------|-------|-------|-------|-------|-------|-------|-------|-------|--------------------|
| Reaction to fire | - | Euroclass A1 | | | | | | | | - | EN 13501-1 |
| Melting point | - | > 1000 | | | | | | | | ٥C | DIN 4102/T17 |
| Maximum service temperature | ST(+) | up to 550/750 | | | | | | | | ٥C | EN ISO 18097 |
| Water soluble chloride ions | | ≤ 3 | | | | | | | | mg/kg | EN 13468 |
| Thermal conductivity in relation to temperature (\mathfrak{G}/λ) EN 14303 | T _m | 150 | 200 | 250 | 300 | 400 | 500 | 600 | 650 | ٥C | EN 12667 |
| | λ | 0.050 | 0.059 | 0.069 | 0.081 | 0.111 | 0.152 | 0.209 | 0.245 | W/mK | |
| Formaldehyde emissions at 350 °C | | | | | | | | | | mg/kg | DIN ISO 16000-3 |
| Fluoride emissions at 350 °C | | ≤ 0,3 | | | | | | | | mg/kg | EN ISO 10304-1 |
| Release of MIC | | ≤ 0,005 | | | | | | | | mg/kg | ISO 17734-1 |
| Surface burning chrasteristics | CFC ¹ | 0 | | | | | | | | - | UL 723 ASTM E84 |
| | FSI ² | 0 | | | | | | | | - | |
| | CSD ³ | | 0.0 | | | | | | | | |
| | SDI ⁴ | | 0 | | | | | | | | |

¹⁾ CFS – Calculated Flame Spread

²⁾ FSI – Flame Spread Index

³⁾ CSD – Calculated Smoke Developed


⁴⁾ SDI – Smoke Developed Index

HANDLING & STORAGE

Knauf Insulation DAP HINF is packed on a wooden or plastic pallet. Packaging is designed for short-term protection only. It is recommended to store the product either indoors, or under a cover and off the ground, for a maximum of up to 12 months.

If the material becomes damp on location, ensure the moisture evaporates before placing the felts into a manufacturing process.

The performance of DAP HNF depends on the customer's manufacturing process. Individual customers must optimize and control their manufacturing process to ensure the material meets the requirements of their manufacturing process and their final product.



Knauf Insulation, d.o.o. Trata 32, 4220 Škofja Loka, Slovenia

Tel: +386 (0)4 5114 100

Fax: +386 (0)4 5114 319

E-mail: oem@knaufinsulation.com

For more info visit:

www.oem.knaufinsulation.com

The investment is co-financed by the Republic of Slovenia and EU with funding allocated by the European Development Fund (Public tender: "Incentives for Research and Development Projects 2"). Details on the European cohesion policy in Slovenia can be found on: www.eu-skladi.si.

All rights reserved, including those of photomechanical reproduction and storage in electronic media. Commercial use of the processes and work presented in this document is not permitted. Extreme caution was taken in assembling the information, texts and illustrations in this document. Nevertheless, errors cannot be entirely ruled out. The publisher and editors assume no legal responsibility or any liability whatsoever for any incorrect information or any consequences thereof. The publisher and editors are grateful for any suggestions for improvement as well as the identification of any errors.

