

KNAUF INSULATION DAP NFS A

July 2023

Needed felts for electric or gas ovens.



PERFORMANCE

Maximum service temperature

DAP NFS A has a maximum service temperature of 750 °C

Thermal insulation

Optimal thermal insulation properties ensure ideal energy efficiency and energy consumption

Certified quality

LGA Certified
Complies with RoHS Directive
Complies with REACH Regulation
RAL
EUCB

APPLICATION

Insulation of **classic or convection, electric or gas ovens** that meet or exceed energy Class A++ / A+ / A standards.

CERTIFICATES



DESCRIPTION

Knauf insulation DAP NEEDED FELT A (DAP NFS A)

products are made of long mineral wool fibres specially needed to form a compact, dimensionally-stable felt with high temperature stability and optimal thermal insulation properties. Due to its insulation performance standards, it can be used for insulating classic or convection, electric or gas ovens that meet or exceed energy efficiency Classes A++ / A+ / A. Product dimensions, sections and facing options can all be adapted to customer requirements.

Owing to the unique fibre bonding process, the felts do not contain organic binders or process aids and therefore comply with LGA test for contaminants, valid for mineral fibres in cookers and ovens. With this special production process we are able to guarantee that no emissions of odorous and/or harmful substances are emitted during the use of ovens and cookers even at the highest temperatures.

Needed felts are tested for the presence of the restricted substances and comply to the RoHS directive and REACH regulation.

BENEFITS

- ✓ High temperature stability and resistance
- ✓ Thermal insulation properties ensure optimal energy efficiency and energy consumption
- ✓ Non-corrosive insulation material (AS Quality)
- ✓ Fire protection (European Class A1) – material melting point above 1000 °C
- ✓ Fire Hazard Classification FHC 0/0
- ✓ No organic binders
- ✓ Emission-free
- ✓ Custom forms and sections
- ✓ Can be laminated with aluminium foil or glass veil

STANDARD

Technical properties of Knauf Insulation DAP NFS A are declared in accordance with EN 14303.

Knauf Insulation DAP NFS A is manufactured in accordance with ISO 9001 Quality Management Systems, ISO 14001 Environmental Management Systems, ISO 50001 Energy Management Systems and ISO 45001 Occupational Health and Safety Management Systems as certified by TÜV Nord.

KNAUF INSULATION DAP NFS A

July 2023

TECHNICAL PROPERTIES

Characteristics	Symbol	Value								Unit	Standard
Reaction to fire	-	Euroclass A1								-	EN 13501-1
Melting point	-	> 1000								°C	DIN 4102/T17
Maximum service temperature	ST(+)	750								°C	EN ISO 18097
Water soluble chloride ions	-	≤10								mg/kg	EN ISO 12624
Thermal conductivity in relation to temperature (ϑ/λ) EN 14303	T _m	150	200	250	300	400	500	600	650	°C	EN 12667
	λ	0.052	0.060	0.069	0.080	0.106	0.139	0.183	0.208	W/mK	
Weighted sound absorption coefficient	α _w	0,5								-	DIN EN ISO 11654
Formaldehyde emissions at 350 °C	-	≤ 2								mg/kg	DIN ISO 16000-3
Fluoride emissions at 350 °C	-	≤ 0,3								mg/kg	EN ISO 10304-1
Release of MIC	-	< 0,005								mg/kg	ISO 17734-1
Surface burning characteristics	CFC ¹⁾	0								-	UL 723 ASTM E84
	FSI ²⁾	0								-	
	CSD ³⁾	0.0								-	
	SDI ⁴⁾	0								-	

¹⁾ CFS – Calculated Flame Spread

²⁾ FSI – Flame Spread Index

³⁾ CSD – Calculated Smoke Developed

⁴⁾ SDI – Smoke Developed Index

HANDLING & STORAGE

Knauf Insulation DAP NFS A is packed on a wooden, plastic or metal pallet. Felts are covered with PE foil or wrapped twice with stretch foil, which is designed for short-term protection only. It is recommended to store the product either indoors, or under a cover and off the ground, for a maximum of up to 12 months.

If the material becomes damp on location, ensure the moisture evaporates before placing the felts into a manufacturing process.

The performance of DAP NFS A depends on the customer's manufacturing process. Individual customers must optimize and control their manufacturing process to ensure the material meets the requirements of their manufacturing process and their final product.



Knauf Insulation, d.o.o.

Trata 32, 4220 Škofja Loka, Slovenia

Tel: +386 (0)4 5114 100

Fax: +386 (0)4 5114 319

E-mail: oem@knaufinsulation.com

For more info visit:

www.oem.knaufinsulation.com

All rights reserved, including those of photomechanical reproduction and storage in electronic media. Commercial use of the processes and work presented in this document is not permitted. Extreme caution was taken in assembling the information, texts and illustrations in this document. Nevertheless, errors cannot be entirely ruled out. The publisher and editors assume no legal responsibility or any liability whatsoever for any incorrect information or any consequences thereof. The publisher and editors are grateful for any suggestions for improvement as well as the identification of any errors.