

# Heraklith A2-C

Non-combustible wood wool  
insulation and soundproof  
board

**Heraklith®**



# Heraklith A2-C

One-layer, non-combustible wood wool board with mineral binder  
Product norm: EN 13168  
EC Certificate of Conformity Reg. Number: K1-0751-CPD-222.0-01-02/12 (E)  
Designation code: 15-35 mm WW-EN 13168 - L1-W1-T1-S2-CS(10)200-C11

## PRODUCT DESCRIPTION

One-layer, non-combustible wood wool board with mineral binder.

## APPLICATION AREA

Thermal insulation of lofts, one- and multi layer partition walls, permanent formwork for eliminating thermal bridges, flooring constructions, sound insulation constructions, ventilated facades (with renders and coverings) It provides an impact resistant surface and a perfect base for renders thanks to the wood wool layer with mineral binder.

## TECHNICAL PROPERTIES

- High fire resistance - A2-s1, d0 - increases the fire safety of buildings
- Excellent heat accumulation
- Very good acoustic properties
- Low vapour resistance
- Excellent construction-biological properties
- Resistant to microorganisms and rodents
- Chemically neutral - no reaction with the surrounding materials
- No mass and dimensional changes in case of temperature differences
- Easy cutting to the requested size and shape
- Very high resistance to mechanical stresses

## PRODUCTION SIZES, PACKAGING UNITS

Thickness	mm	15	25	35
Average mass	kg/m <sup>2</sup>	12,0	14,0	17,0
Packaging unit	pc/pallet	70	40	29
Amount of the package	m <sup>2</sup> /pallet	84,0	48,0	34,8
Length	mm	2 000*		
Width	mm	600		

Transportation: on pallets. Packaging: wrapped in foil, strapped on two positions.

\*Boards can be ordered in half length (1000 mm)

## TECHNICAL DETAILS

Properties	Sign	Description/Data			Unit	Norm
Fire class	-	A2-s1, d0			-	EN 13501-1
Thermal conductivity	$\lambda_D$	0,070			[W/mK]	EN 13168
Thickness	d	15	25	35	[mm]	
Thermal resistance - declared value	$R_D$	0,20	0,35	0,50	[m <sup>2</sup> K/W]	EN 13168
Compression strength	$\sigma_m$	≥ 200			[kPa]	EN 826
Vapour diffusion resistance factor	$\mu$	5			-	EN 12086

### Dimensional stability and tolerances of WW boards

Due to the organic component of wood wool boards slight deviations in the size cannot be excluded. Likewise, the panels also shrink and expand if there is strongly fluctuating air humidity.

• Dimensional stability in standard climatic conditions is 0,5% for length (± 10 mm for 2000 mm boards) and for width (± 2,5 mm for 600 mm wide boards).

Therefore, special attention must be given to the temperature and air humidity during installation (if necessary heat, ventilate, or dehumidify the air under constant monitoring) in order to ensure the required installation conditions.

• Production tolerance for the 2000 mm nominal dimensions is +5/-10 mm; for 1000 mm lengths +3/-5 mm, for width is ± 3 mm according to EN 13168 point 4.2.2.

### Installation and system conditions

• The installation of WW products (Heraklith homogeneous boards, Heratekta and Tektalan composite boards) must be carried out under controlled humidity and temperature conditions.

• Only install panels in rooms, where the following conditions are ensured: for heated or air-conditioned rooms, the maximum relative air humidity must be between 40% and 75%, the temperature must not be below +7°C or above +30°C.

• If WW products are to be installed in rooms with central heating, or in rooms with conditions significantly different from normal conditions we recommend acclimatising the boards for at least 48 hours days in a room with the same climatic conditions.

All rights reserved, including those of photomechanical reproduction and storage in electronic media. Commercial use of the processes and work activities presented in this document is not permitted. Extreme care was observed when putting together the information, texts and illustrations in this document. Nevertheless, errors cannot be completely ruled out. The publisher and editors cannot assume legal responsibility or any liability whatever for incorrect information and the consequences thereof. The publisher and editors will be grateful for suggestions for improvement and notification of any errors.

### Knauf Insulation Kft.

H-8924 Alsónemesapáti, Ipartelep

H-8901 Zalaegerszeg Pf. 303.

Tel.: +36 92 550 900

Fax: +36 92 550 901

info.hu@knaufinsulation.com

www.knaufinsulation.hu

Heraklith® is a registered trademark of

**KNAUFINSULATION**  
it's time to save energy