

FACTORY CLAD 44 ROOF

November 2018

APPLICATIONS



DESCRIPTION

Specifically designed to be used in roofing of metal buildings, Factory Clad 44 Roof is a light weight thermal insulation.



PERFORMANCE

Thermal

Conductivity: 0.044W/mK

Fire

Classification: Does not exceed 25 Flame Spread, 50 Smoke Developed when tested in accordance with ASTM E84. (FSK, WMP 10)

FactoryClad 44 with MP facing is not recommended for application areas where fire might be a concern (MP)

BENEFITS

- ✓ Exceptionally high tear strength
- ✓ Provides thermal and acoustic performance
- ✓ Cost effective
- ✓ Lightweight, easy to handle and install

SPECIFICATIONS

Facing	Thickness (mm)	Length (m)	Width (mm)	Area per pack (m ²)	Thermal Conductivity (W/m.K)	R Value (m ² .K/W)	Density kg /m ³	Rolls per pack
FSK	100	10	1100	11	0.044	2.27	10	1
FSK	50	20	1100	22	0.044	1.14	10	1
MP	50	20	1100	22	0.044	1.14	10	1
MP	25	30	1100	33	0.044	0.57	10	1

All dimensions are nominal.

CERTIFICATION



FACTORY CLAD 44 ROOF

November 2018

ADDITIONAL INFORMATION

Application

FactoryClad 44 Roof are used for the thermal and acoustic insulation of roofs in profiled metal clad buildings and portable buildings. FactoryClad 44 Roof are manufactured 1100mm wide to suit commonly used rail and bracket systems and in long lengths, making them particularly suitable for use in twin skin profiled metal cladding systems and standing seam roofs.

Standards

FactoryClad 44 Roof is manufactured in accordance with BS EN 13162, OHSAS 18001 Occupational Health and Safety Management Systems, ISO 14001 Environmental Management Systems, and ISO 9001 Quality Management Systems, as certified by Bureau Veritas.

Certification

FactoryClad 44 Roof are certified under UL 723, DCL Product Conformity, EUCEB for conformity of fibres produced with the requirements of Note Q of the Regulation (EC) No 1272.2008 of EP and EC, EUROFINS Indoor Air Quality Gold, SASO Product Conformity.

Durability

FactoryClad 44 Roof is odourless, rot proof, non-hygroscopic, does not sustain vermin and will not encourage the growth of fungi, mould or bacteria.

Environmental

FactoryClad 44 Roof represents no known threat to the environment and has zero Ozone Depletion Potential and zero Global Warming Potential.

Water Vapor Permeance

Factory Clad 44 Roof (FSK) have a maximum water vapor permeance of 0.02 perms as per ASTM E96, Procedure A.

Factory Clad 44 Roof (WMP10) have a maximum water vapor permeance of 0.02 perms as per ASTM E96, Procedure A.

Factory Clad 44 Roof (MP) have a maximum water vapor permeance of 0.02 perms as per ASTM E96, Procedure A.

Handling and storage

FactoryClad 44 Roof is easy to handle and install, being lightweight and easily cut to size, where necessary. It is supplied enclosed in polythene which is designed for short term protection only. For longer term protection on site, the product should be stored either indoors, or under cover and off the ground. FactoryClad 44 Roof should not be left permanently exposed to the elements.



Knauf Insulation mineral wool products made with ECOSE Technology® benefit from a no added formaldehyde binder, which is up to 70% less energy intensive than traditional binders and is made from rapidly renewable bio-based materials instead of petroleum-based chemicals. The technology has been developed for Knauf Insulation's glass and rock mineral wool products, enhancing their environmental credentials without affecting the thermal, acoustic or fire performance. Insulation products made with ECOSE Technology® contain no dye or artificial colours.

Knauf Insulation LLC

Mussaffah ICAD 1, P.O.Box 34332,
Abu Dhabi, United Arab Emirates

Customer Service: +971 2 551 2453 Technical Support & Marketing: +971 2 551 2453 Email: technicalsupport@kei.ae

All rights reserved, including those of photomechanical reproduction and storage in electronic media. Extreme caution was observed when putting together and processing the information, texts and illustrations in this document. Nevertheless, errors cannot quite be ruled out. The publisher and editors cannot assume legal responsibility or any liability whatever for incorrect information and the consequences thereof. The publisher and editors will be grateful for improvement suggestions and details of possible errors pointed out.

KINE3490DAT - V1118

challenge.
create.
care.