

## POWER-TEK BD 350\*



July 2020

\*data specific to UK manufactured product only

### APPLICATION RANGE



### DESCRIPTION

Power-teK BD 350 is a non-combustible Mineral Wool slab, designed to resist high temperatures and provide thermal and acoustic performance, for use in applications up to 350 °C.

Generic Green Guide rating A+

### TECHNICAL DATA

Max. service temperature	350 °C (EN 14706)
Reaction to fire	A1 (EN 13501-1)
Nominal density	45 kg/m <sup>3</sup> (EN 1602)
Declaration of performance*	<a href="http://dopki.com/T4208KP">http://dopki.com/T4208KP</a>

\*for detailed information on DoP please check the product label

Description	Sign	Description/data							Unit	Standard
Thermal conductivity depending on temperature	θ	50	100	150	200	250	300	350	°C	DIN EN 12667
	λ	0.041	0.050	0.062	0.076	0.094	0.113	0.136	W/(mK)	
Water soluble chloride ions (AS quality)	-	≤ 10							ppm	EN 13468
Total water absorption	W <sub>p</sub>	≤ 1							kg/m <sup>2</sup>	EN 1609
Water vapour diffusion resistance value	μ	1							k Pa·s/m <sup>2</sup>	EN 12086
Silicone free	-	Produced without addition of silicone oil							-	-
Melting point of fibres	θ	≥ 1000							°C	DIN 4102-17
Longitudinal air flow resistance	r	≥ 5000							-	EN 29053
Specific heat capacity	c <sub>p</sub>	1030							J/(kgK)	EN ISO 10456
Designation code	-	MW-14303-TS-ST(+)-350-WS1							-	EN 14303

Declared material properties are obtained in the production process and ensured by the factory production control in accordance with the European Standard at the time of manufacture. Observing storage and handling guidelines will maintain performance within published tolerances.

### CERTIFICATES



challenge.  
create.  
care.

# POWER-TEK BD 350



July 2020

## ADDITIONAL INFORMATION

### Application

The product is recommended for thermal, fire and sound insulation of the defined applications within technical insulation.

Boilers and tanks, Machine insulation, Containers, Chimneys, Sound insulations, Thermally resistant constructions, Drying systems, Air handling units, Industrial finishing, Vessels

### Handling

Knauf Insulation products are easy to handle and easy to install. They are supplied in suitable packaging materials to balance necessary transport protection with sustainable recycling options. Packaging is not designed for long-term storage or exposure to harsh weather conditions. Further product information is mentioned on every pack.

### Storage

For longer-term protection on site we recommend storing the product either indoors or alternatively under a roof cover and off the ground. If covered storage is not available, products can be stored outside (open-air-storage) if placed off the ground (keep palletized) and covered with plastic hood (foil), for a maximum of up to 6 months from the date of delivery. Outdoor storage is not recommended during particularly humid months with large fluctuations in temperature.

### Note

Also available with aluminium facing.

### Standard formats\*

Thickness	40, 50, 75, 100 mm
Width	600 mm
Length	1200 mm

\* Other dimensions on request.

### ISO STANDARDS

Knauf Insulation products are produced according to four of the most important International Management Standards for sustainability ISO 9001 (Quality Management), ISO 14001 (Environmental Management), ISO 50001 (Energy Management) and ISO 45001 (Health and Safety Management), all certified by Tüv Nord.

### Knauf Insulation Ltd

Chemistry Lane  
CH5 2DA Pentre - Queensferry

Flintshire Wales  
United Kingdom

All rights reserved, including those of photomechanical reproduction and storage in electronic media. Commercial use of the processes and work presented in this document is not permitted. Extreme caution was taken in assembling the information, texts and illustrations in this document. Nevertheless, errors cannot be entirely ruled out. The publisher and editors assume no legal responsibility or any liability whatsoever for any incorrect information or any consequences thereof. The publisher and editors are grateful for any suggestions for improvement as well as the identification of any errors.