

KNAUF INSULATION BL D120

February 2020



Knauf Insulation BL D120 are blocks made of rock mineral wool. Blocks can be used for different types of converting, mostly to pipe sections. Because of their specific properties, primarily excellent fire protection, they are, after converting, used for thermal and fire protection.

PERFORMANCE

| Reaction to fire | A1 (EN 13501-1) | |
|----------------------------|--------------------------|--|
| Density | ca. 120 kg/m³ | |
| Declaration of performance | http://dopki.com/R4305JP | |

| Description | Sign | Description/data | Unit | Standard |
|---|----------------|------------------|----------|--------------|
| Melting point of fibres | | > 1000 | °C | DIN 4102-17 |
| Thermal conductivity declared | λ | 0,037 | W/(mK) | EN 12667 |
| Water absorption | | WS | | EN 12086 |
| Water soluble cloride ions (on request) | | ≤ 10 | mg/kg- | EN 13468 |
| Longitudinal air flow resistance | r | ≥30 | kPa s/m² | EN 29053 |
| Specific heat capacity | C _p | 1030 | J/(kgK) | EN ISO 10456 |

Declared material properties are obtained in the production process and ensured by the factory production control in accordance with the European Standard at the time of manufacture. Observing storage and handling guidelines will maintain performance within published tolerances.

CERTIFICATE













KNAUF INSULATION BL D120

February 2020

ADDITIONAL INFORMATION

Application

Insulation blocks for further converting processes

Handling

Knauf Insulation products are easy to handle and easy to install. They are supplied in suitable packaging materials to balance necessary transport protection with sustainable recycling options. Packaging is not designed for long-term storage or exposure to harsh weather conditions. Further product information is mentioned on every pack.

Storage

For longer term protection on site it is recommended to store the product indoors or alternatively under a roof and without direct contact to the ground (keep palletised).

Standard format:*

| Thickness | 100 - 200 mm |
|-----------|--------------|
| Width | 600 mm |
| Length | 1000 mm |

^{*}Other dimensions on request

ISO STANDARDS

Knauf Insulation products are produced according to four of the most important International Management Standards for sustainability ISO 9001 (Quality Management), ISO 14001 (Environmental Management), ISO 50001 (Energy Management) and OHSAS 18001 (Health and Safety Management), all certified by Tüv Nord.

Knauf Insulation d.o.o

Varaždinska 140 42220 Novi Marof Croatia

All rights reserved, including those of photomechanical reproduction and storage in electronic media. Commercial use of the processes and work presented in this document is not permitted. Extreme caution was taken in assembling the information, texts and illustrations in this document. Nevertheless, errors cannot be entirely ruled out. The publisher and editors assume no legal responsibility or any liabilitywhatsoever for any incorrect information or any consequences thereof. The publisher and editors are grateful for any suggestions for improvement as well as the identification of any errors.

